

Glazed Ceramic Wall Tile

TOUCH

Technical Specifications

Technical Characteristics	ASTM Test	Standard	Result
Water Absorption %	ASTM C373	>10% ; <17%	Pass
Caliber Range	ASTM C499	<ul style="list-style-type: none"> •Length 600 mm: ± 1.2 mm •Width 200 mm: ± 0.5 mm 	Pass
Dimensionality (Warpage Diagonal)	ASTM C485	Min -0.60 mm; Max +0.8 mm	Pass
Dimensionality (Warpage Edge)	ASTM C485	<ul style="list-style-type: none"> •Length 600 mm: Min -1.3 mm; Max +0.80 mm •Width 200 mm: ± 1.3 mm 	Pass
Wedging	ASTM C502	<ul style="list-style-type: none"> •Length 600 mm: ± 1.2 mm •Width 200 mm: ± 0.5 mm 	Pass
Crazing Resistance	ASTM C424	Conform	Pass
Surface Quality	EN ISO 10545-2	A minimum of 95 % of tiles examined (Total flooring), shall be without visible defects at 1 meter with daylight reflection.	Pass

Acacia Tile Inc.

5463 50th Ave • Delta, BC V4K2A1 • CA

604-757-0986

info@acaciatile.com